

LABITEX WB 648 B

Product description:

Glossy water-dispersional varnish with barrier properties in relation to edible fats and oils. Designed for printing food packaging, including packaging for direct contact with food.

Physical characteristics:

Flash point:	> 100°C
Viscosity (20 ⁰ C):	30±5 (DIN-4)
Solid content:	45±5%
pH:	8,4±0,2
Gloss (60 ⁰):	> 50
Rub resistance:	High
Hot stamping:	Testing required
Glueability (without special glue):	Yes
Freeze stability:	Testing required

Product features:

- High barrier properties in relation to food fats (fat resistance).
- Suitable for direct contact with food.

Substrate:

Paper	*	*** Perfect suitable
Cardboard	***	** Suitable
Non-absorbent substrates ¹	X	* Tests recommended
Treated non-absorbent substrates ¹	X	x Not suitable

¹Label paper, laminated cardboard and synthetic substrates (PP, PE, PVC, OPP and etc.)

Application:

- Equipment: Offset press coating unit.
- To ensure good barrier properties, a single application with a layer of at least 6-8 g / m² of varnish “in wet way” (anilox of at least 20 cm³ / m²) is recommended. Twofold application by anilox of a smaller volume (about 12 cm³ / m²) is allowed.

The indicator is highly dependent on the absorbency of the sealed base. Preliminary tests of barrier properties should be carried out before printing the main print run

STIR COATING WELL BEFORE USE!

Version dated 19/09/2019

Prior tests are recommended before any commercial work.

The information contained herein is based on our knowledge, true and correct. Any recommendations are made without guarantee, as the conditions of use are beyond our control. Our technical department may be contacted for further information.

WATER BASED COATINGS APPLICATION GENERAL GUIDELINE

Application viscosity:	As supplied.
Coating diluent:	Water. 2% maximum.
Coating drying:	Hot air flow 50-60°C. The temperature in the pallet should be below 35°C.
Equipment clean-up:	Liquid coating – warm water. Dried coating – ethyl acetate or another solvent.
Coating and inks:	It is not recommended to varnish oil based offset paints based on the following unstable pigments: Warm Red, Rhodamine, Purple, Purple, Blue Reflex, Blue 072. In this case, use special resistant colors.

It is possible to apply the UV-coating on top of the Labitex WB varnish dried film. For the best adhesion of the UV coating special primer is recommended.

Prior tests are recommended!

Storage:	The recommended storage temperature is 18-22°C. Guaranteed shelf life is 12 months in closed original packaging.
Safe handling:	All works should be proceeded in the ventilated working area. For more information, please, see the MSDS.

STIR COATING WELL BEFORE USE!

Notes

- All information provided in this Technical Data Sheet (TDS) including the recommendations for application is based on our current knowledge and experiences.
- The information about technical specifications (such as slip angle or reactivity) is based on our examinations under laboratory conditions and the mentioned values can differ from the practice.
- This document is provided for informational purposes only and do not release users from carrying out their own tests and trials.
- We reserve the right to change product properties according to the newest requirements of technical progress, amendments and additions to the list of restricted raw materials. These changes do not bring negative impact on the technical characteristics of the product.

Version dated 19/09/2019

Prior tests are recommended before any commercial work.

The information contained herein is based on our knowledge, true and correct. Any recommendations are made without guarantee, as the conditions of use are beyond our control. Our technical department may be contacted for further information.