

"BALTINK" SIA tel: +371 24 422 737 info@baltink.eu www.baltink.eu



## Labitex UV 8 MAT

## **Product description:**

Clear acrylate UV varnish with a high level of matte effect. One-component product, ready to use. It is applied by roller machines of all types on surfaces previously primed with transparent UV primers. It is used as a top coat for flat elements of furniture for indoor use. It has a silky touch surface and good resistance to chips and scratches.

<b>Physical charecteristics:</b> Viscosity 20 <sup>0</sup> C: Specific gravity at 20 <sup>0</sup> C: Solid content:	150±15 B3-4 1,15±0,1 100%
Application:	
Machine mode:	According to the instructions for the car; all components of the machine, including shafts and hoses, must be adapted to work with UV polymerization materials. Before use, the varnish should be mixed.
Viscosity:	As in delivery. The viscosity of UV materials is highly temperature dependent. Before starting work, it is necessary to bring the UV materials to operating temperature (18-220C) and maintain for 3-4 hours. Stir thoroughly before use. It is possible to heat the varnish in order to lower the viscosity and improve spreading (do not heat the varnish above 400 $^{\circ}$ C). In some cases (for example, when applied by roller machines with a laser notch), it is possible to dilute with a special thinner.
Polimerization:	Tunnel drying of high-power UV lamps. For one lamp 80 W/cm ( $\lambda = 360$ nm), the conveyor speed is not more than 4-5 m/min.
Varnish consumption:	Repeated application of varnish layer to layer is not allowed! The application volume is $15-20 \text{ g/m}^2$ .
In case of varnishing:	<ul> <li>-painted surfaces with increased content wax or silicone additives;</li> <li>-water and oil varnishes that are not special primers;</li> <li>- Laminated with hydrophobic non-absorbent plastics surfaces may cause problems with adhesion and wetting of the varnished material.</li> </ul>
Manipulations with varnished surfaces:	Work with varnished surfaces can be carried out 30 minutes after applying varnish. The final properties (strength, adhesion and matte effect) acquire the varnish film after ripening within 12-16 hours.
Storage of varnish:	When air temperature changes, the viscosity of UV varnishes changes dramatically; in order to avoid problems in work, we recommend storing UV varnishes at a
Special precautions:	temperature of 18-22°C. Shelf life: 6 months in sealed packaging. Avoid any contact of the varnish with the skin. All work should be carried out in a ventilated room.

## **STIR WELL BEFORE USE!**

Version of 03.08.2019