

"BALTINK" SIA tel: +371 24 422 737 info@baltink.eu www.baltink.eu





## RADIORPLUS high transfer

**Description:** 

RADIORPLUS high transfer - Gold and PANTONE® series Shades

available:

Pale gold, Rich pale gold and Rich gold PANTONE® 871 to PANTONE® 876

<u>Properties:</u> RADIORPLUS high transfer inks provide <u>good gloss and metallic effect.</u>

Formulae based on a 2 µm pigment with commensurate tack/viscosity provide excellent

printability with improved transfer and enhanced dot definition.

Particularly suitable for High Speed presses.

Versatile inks suitable for a wide variety of applications: fine type and solids

Application: Conventional Sheetfed Offset

ptg Speed: 12000 - 15000 iph

<u>Coverage:</u> 1,5 - 2 g/m<sup>2</sup> depending on substrate

Fountain solution: Recommended pH: 5 - 5,5

<u>Characteristics:</u> Viscosity (Laray viscometer, 25°C): 90 – 110 Poises

Density: 1,3 – 1,4

Brilliance (Micro-Tri-Gloss, 60°): ≥ 70

PANTONE\* series ≥ 60

The data above are subject to the shade

<u>Substrates:</u> Paper and board

Shelf life: 12 months

Remaining ink should be sprayed or covered with skin paper

Storage conditions: Store between 15°C and 25°C

Packaging: 1 Kg

**Remarks:** Mix thoroughly before use

<u>RADIORPLUS high transfer - Gold</u> may be film laminated and compatible with a wide range of varnishes: offset, acrylic emulsions and UV. However, in order to ensure adhesion with

UV, it is imperative that an acrylic primer is employed.

Varnishability depends on substrate absorbency and flexibility of the lacquer.

Varnishing and laminating operations affect dramatically the gloss and metallic effect of the

ink.

Prior tests are recommended before undertaking any commercial work Our technical department may be



"BALTINK" SIA tel: +371 24 422 737 info@baltink.eu www.baltink.eu



contacted for further information

We reserve the right to change products characteristics and technical data following new developments. The information contained herein is to the best of our knowledge true and correct. Any recommendations are made without guarantee, express or implied, as the conditions of use are beyond our control

RADIOR France TDS 114 - Gold	Version 4	Revision date: 08/01/13
------------------------------	-----------	-------------------------